



Pulp characteristic

RAFINED MECHANICAL WOOD PULP -UNBLEACHED (RMP) & BLEACHED (BRMP)

Property	Method	Unit	Target (RMP)	Target (BRMP)
CSF	ISO 5267/2	ml	360 ±40	300±40
Brightness R457	ISO 2470	%	40-45	53-56
Bulk	ISO 534	cm ³ /g	>2,8	>2,7
Breaking length	ISO 1924-3	m	>1200	>1400
Tensile index	ISO 1924-3	Nm/g	>11.8	>13,7
Shives, Brecht-Holl 0,20mm	Data sheet VI/1/66	%	<2,0	<1,5
Dryness	ISO 287	%	88 ± 2	88 ± 2

Sample preparing:

ISO 5263 Laboratory wet disintegration; ISO 5269/2 Preparation of laboratory sheets for physical testing-Part 2. Rapid-Köthen method; ISO 4119 Determination of stock concentration


Packaging information

Bale sizes

Length: 870 mm

Width: 650 mm

Weight: 170 ±5 kg



Container transport unit sizes:

4 bales per unit

Length: 870 mm

Height: 2200 ±100 mm

Weight: 680 ±20 kg

General information

Wood species: Fir/Spruce

Pulp is flash dried

Bleaching: Peroxide, totally chlorine free (TCF)

Wrapping: Unbleached kraft paper (for unbleached RMP)
Bleached kraft paper (for bleached RMP)

Certificates

