



"drvenjača" d.d. - fužine



Pulp characteristic

RAFINED MECHANICALWOOD PULP -UNBLEACHED (RMP) & BLEACHED (BRMP)

Property	Method	Unit	Target (RMP)	Target (BRMP)
CSF	ISO 5267/2	ml	360 ±40	300±40
Brightness R457	ISO 2470	%	40-45	53-56
Bulk	ISO 534	cm ³ /g	>2,8	>2,7
Breaking lenght	ISO 1924-3	m	>1200	>1400
Tensile index	ISO 1924-3	Nm/g	>11.8	>13,7
Shives, Brecht-Holl 0,20mm	Data sheet VI/1/66	%	<2,0	<1,5

Sample preparing:

ISO 5263 Laboratory wet disintegration; ISO 5269/2 Preparation of laboratory sheets for physical testing-Part 2.Rapid-Köthen method; ISO 4119 Determination of stock concentration


Packaging information

Bale sizes

Length: 870 mm

Width: 650 mm

Weight: 170 ±5 kg



Transport unit sizes:

(4 bales per unit)

Length: 870 mm

Height: 2200 ±100 mm

Weight: 680 ±20 kg

General information

Wood species: Fir/Spruce

Bleaching : Peroxide, totally chlorine free (TCF)

Pulp is flash dried

Wrapping: Bleached kraft paper

Certificates



The mark of responsible forestry



Drvenjača d.d. Donje selo 62, HR-51322 Fužine, Croatia • Phone: + 385 51 830 100 • E-mail: drvenjaca@drvenjaca.hr

www.drvenjaca.hr